

# The Suitability of Crushed Over Burnt Bricks as Coarse Aggregate for Concrete

Mr. Pranit Padalkar<sup>1</sup>, Prof. V.G. Khurd<sup>2</sup>

<sup>1</sup>Student, M.Tech, Dept. of Civil Engineering, Sanjay Ghodawat University, Kolhapur.

<sup>2</sup>Professor, Dept. of Civil Engineering, Sanjay Ghodawat University, Kolhapur

\*\*\*

**Abstract**— Concrete is a versatile engineering material consisting of cementing substance, aggregates, water and often controlled amount of entrained air. It is initially a plastic, workable mixture which can be molded into a wide variety of shapes when wet. The strength is developed from the hydration due to the reaction between cement and water. The products, mainly calcium silicate, calcium aluminates and calcium hydroxide are relatively insoluble which bind the aggregate in a hardened matrix. The primary goal of the research is to investigate and evaluate the feasibility of employing crushed over burned brick aggregate as an alternative to costly traditional stone aggregate in concrete in order to minimize production costs, construction costs, and dead weight of a building structure. The research was conducted to study the suitability of crushed over burnt bricks as alternative coarse aggregates for concrete production. Tests were carried out to determine the physical properties of the crushed over burnt bricks aggregates. Values of 0%, 25% 50%, 75% and 100% were obtained for aggregate crushing value, aggregate impact value and aggregate water absorption respectively

**Keyword:** Coarse-aggregates, Concrete, Crushed over burnt bricks, Suitability, ANSYS

## 1. INTRODUCTION

Cement, water, coarse and finely ground, and mortar are added to make concrete (if needed). The great advantage of concrete is that it can be built to withstand extreme conditions. The goal is to assemble these components in precise proportions to produce concrete that is easy to transport, stand, assemble, and finish, and that will set and harden to produce a solid and durable product. The amount of each component (cement, water, and aggregates) affects the properties of the solid concrete. Concrete mixes are intended to produce concrete that can be easily installed at very low cost. In order to produce strong and durable concrete, the concrete must work and harden if it is plastic, then set and firm. The design of the mix should take into account the location where the concrete will be used, such as exposure to seawater, trucks, vehicles, forklifts, pedestrians, or hot and cold temperatures. Concrete is made up of Cement, Water, Solid and Fine Joints, and composite materials. The proportions of each component in the mixture influence the final properties of the solid concrete. Weight is

a very accurate measure of weight. Volume measurement is not so bad, yet it is enough for small projects. Concrete is a flexible engineering material made up of cement, scales, water, and a controlled part of the air inlet. It has risen to the point of being in demand in modern architecture. Concrete is always selected and considered suitable wherever energy, fire resistance, and durability are required. When wet, it becomes plastic, a functional substance that can be molded into a variety of shapes. The mixture between cement and water produces hydration, which leads to the formation of energy. The raw materials used to make it, cement and mortar, have an impact on both quality and construction costs. Aggregates are usually less expensive than cement and cost more than 70% of the concrete volume. Construction costs are also affected by the availability and proximity of the total construction site. The immature materials used to make cement, sand, and composites have an impact on both quality and construction costs. Aggregates are usually less expensive than cement and cost more than 70% of the concrete volume. Construction costs are also affected by the availability and proximity of the total construction site. However, when quantity is scarce and there is an urgent need to conserve natural resources for long-term growth and to conserve resources for the benefit of future generations, this involves the use of some of the rigid components provided locally. The bat or brick kiln found in the making of bricks is one of the rough collections. Heat-treated concrete such as rough clusters have applications such as lightweight concrete, lightweight mixtures, load reduction for buildings with large structural features, PCC function, and floors. Burnt bricks cannot be used in road construction if they fail impact and abrasion tests.

### 1.1. Over Burnt Brick Aggregate

The aggregate of overheated bricks is a useful asset for bare concrete works and fortified works where the pressure is not too high. Prior to use, the aggregate of the bricks should be filled with water to avoid the absorption of mixing water, which is required for the cement hydration and the setting and durability of the concrete. The aggregate of crushed stone is more resistant to fire and absorbs noise than a combination of bricks. Extremely hot bricks are used in concrete as part of a solid natural mixture. The practical and mechanical features of the Over Burn Brick design were used to achieve this goal. The type of waste bricks included in this

study are found during the construction of various buildings in the large Kolhapur area, and this type is tested to determine its mechanical properties before being hired. Conventional concrete models are cast and tested to match their results with traditional mixtures. A mixture of burnt bricks for waste construction.

## 2. ANALYTICAL TESTING RESULTS

### 2.1 Mix Design

The main goal of concrete mixing design is to determine the best concentrations of the various concrete materials, resulting in new concrete with desirable performance and strong concrete with the required compression strength and durability. Mixtures should also meet the additional condition of using the least amount of cement possible so that the cost of concrete is kept to a minimum.

The following basic data are required to be satisfied for the design of concrete mix.

1. Characteristic compressive strength of concrete at 28 days.
2. Degree of workability.
3. Limitations on the water cement ratio and the minimum cement content to ensure adequate durability as per IS: 456 – 2000 [80].
4. Type and maximum size of aggregate to be used.
5. Standard deviation of compressive strength of concrete.
6. Degree of quality control.
7. Type of exposure.
8. Specific gravity of cement, fine and coarse aggregate.
9. Fineness modulus of fine and coarse aggregate.

#### Design steps

- I. From known characteristic compressive strength, the target mean strength is to be estimated by using the formula,  $F_t = F_{ck} + S \times t$ , Where 'S' is Standard Deviation and 't' is a coefficient
- II. The water cement ratio selected as per Table-5, IS: 456-2000 [80] based on the exposure condition.
- III. The water content is selected from Table-2, IS: 10262-2009 [64] based on the maximum nominal size of aggregates

IV. After, calculating water content, cement content is calculated from the water- cement ratio and water content

V. Proportion of volume of coarse and fine aggregate

Volume of coarse aggregate corresponding to nominal maximum size of aggregates and fine aggregate confining to the specific zone as per IS: 383 - 1970 is calculated from Table-3, IS: 10262:2009.

VI. Calculation of Mix proportions

- Volume of the concrete (a) =  $1\text{m}^3$
- Volume of cement (b) =  $\frac{\text{mass of the cement}}{\text{specific gravity of the cement}} \times (1/1000)$
- Volume of water(c) =  $\frac{\text{mass of water}}{\text{specific gravity of water}} \times (1/1000)$
- Volume of all in aggregate (d) =  $[a - (b + c)]$
- Mass of coarse aggregate =  $d \times \text{volume of coarse aggregate} \times \text{specific gravity of coarse aggregate} \times 1000$
- Mass of fine aggregate =  $d \times \text{volume of fine aggregate} \times \text{specific gravity of fine aggregate} \times 1000$

Table 1 Mix proportions of all Mixes

Grade of concrete	Cement (kg/m <sup>3</sup> )	Fine aggregate (kg/m <sup>3</sup> )	Coarse Aggregate (kg/m <sup>3</sup> )	Water(Lt)
M20	347	550	1120	180
M25	385	578	1155	212



Fig 1 Crushed Over Burnt Bricks



Fig 2 Crushed Over Burnt Bricks

### 2.2 Density of concrete

Concentration of concrete, also known as the weight of a cubic meter of concrete, is necessary to determine the strength of the concrete in advance. As the concrete density decreases, so do the voids and, consequently, the strength. Immediately after mixing the layers, the scale is filled with freshly mixed concrete.

Density = Weight of the Measure / Volume of the measure

Table 2 Results For Density of concrete

Percentage Replacement	0%	25%	50%	75%	100%
M20 (Kg/m <sup>2</sup> )	2610	2515	2400	2255	2125
M25 (Kg/m <sup>2</sup> )	2746	2682	2591	2400	2274

### 2.3 Compressive strength of concrete

The concrete was filled into the mould in layers approximately of 5cm thick. Each layer was compacted by vibrating with a vibrating table till the desired compaction was achieved.

$$F_{ck} = P/A$$

Where, P = Maximum load applied on the specimen

A = area of cross-section of the specimen on which the load is applied.

Table 3 Compressive strength of concrete

Percentage Replacement	0%	25%	50%	75%	100%
M20 (N/mm <sup>2</sup> )	26.77	26.56	18.37	11.55	7.88
M25 (N/mm <sup>2</sup> )	31.71	31.61	22.04	13.98	10.21

### 3. SOFTWARE ANALYSIS RESULTS

RCC short c/s column 300mmX300mm with 3760mm in height, enhanced by 4 HYSD500 bars with links in diameter 25mm with 8mm ties The HYSD500 should be checked in the ANSYS programme for four leg straps with a load of 1700 KN and the thermal analysis should also be performed to verify the impact of columns after temperature stresses.

Table 4 Models

MODEL 1	COLUMN WITH BBA 0%
MODEL 2	COLUMN WITH BBA 25%
MODEL 3	COLUMN WITH BBA 50%
MODEL 4	COLUMN WITH BBA 75%
MODEL 5	COLUMN WITH BBA 100%




Fig 3 model as required





Fig 4 Evaluation Results


### 3.1 Total Deformation mm



Graph 1 Total Deformation mm

The graph above shows the result for Total Deformation for column with Replacement of BBA with variations of 0%, 25%, 50%, 75%, and 100% and compares the results. The results show that Total Deformation for 0%, 25%, and 50% is less than 75% and 100% is around 10-20%.


### 3.2 Maximum Principal Elastic Strain Mpa



Graph 2 Maximum Principal Elastic Strain Mpa

The graph above shows the result for Maximum Principal Elastic Strain for column with Replacement of BBA with variations of 0%, 25%, 50%, 75%, and 100% and compares the results. The results show that Maximum Principal Elastic Strain for 0%, 25%, and 50% is less than 75% and 100% is around 5-10%.

### 3.3 Maximum Principal Elastic Stress Mpa



Graph 3 Maximum Principal Elastic Stress

The graph above shows the result for Maximum Principal Elastic Stress for column with Replacement of BBA with variations of 0%, 25%, 50%, 75%, and 100% and compares the results. The results show that Maximum Principal Elastic Stress for 0%, 25%, and 50% is less than 75% and 100% is around 10-15%.

### 5. CONCLUSION

Concrete is being used more and more in today's society to fulfil the rapid rise of infrastructure needs. This fast use of concrete in the construction industry has resulted in a severe problem of resource depletion, such as sand, coarse aggregate, and so on. Furthermore, the concrete is vulnerable to fire accidents owing to a variety of factors such as natural catastrophes, power supply short circuits, gas leaks, and so on, resulting in concrete deterioration. A systematic review of the literature revealed that detailed research on the behaviour of recycled brick aggregate concrete at higher temperatures is essentially non-existent, leaving confusion about its applicability. As a result, the current study is being conducted to better understand the behaviour of recycled brick aggregate concrete when subjected to high pressures and temperatures.

Burn brick aggregate (BBA) concrete was made by replacing the granite aggregate with 25, 50, 75, and 100% by weight certified recycled brick aggregate. The density and compressive strength of fresh and hardened recycled brick aggregate concrete were studied at room temperature in order to optimize the percentage replacement of recycled brick aggregate in order to achieve the desired M20 and M25 grade BBA concrete in the form of density and compressive strength tests. For analytical findings, we examined models in FEM software ANSYS with high load values up to 1800Kn and concluded that the BBA replacement 25% and 50% have economic results, thus we may advise aggregate repayment to BBA up to 50% in concrete. The following results sum up all of the findings

## 6. REFERENCES

- [1] Ivana Kesegic, Ivanka Netinger and Dubravka Bjegovic "Recycled Clay Brick as An Aggregate for Concrete: Overview", ISSN, (2008), 1330-3651, UDC/UDK 691.322: 628.4.036.
- [2] Mohammad Abdur Rashid, Tanvir Hossain, and M. Ariful Islam "Properties of higher strength concrete made with crushed brick as coarse aggregate", Journal of Civil Engineering (IEB), (2009), 37(1).
- [3] Ksenija Jankovic, Dragan Nikolic, Dragan Bojovic, Ljiljana Loncar and Zoran Romakov "The Estimation of Compressive Strength of Normal and Recycled Aggregate Concrete", Facta Universitatis, (2011), Vol. 9, No 3, 2011, pp. 419 - 431.
- [4] Gopinandan Dey and Joyanta Pal "Use of Brick Aggregate in Standard Concrete and Its Performance in Elevated Temperature", International Journal of Engineering and Technology, (2013), Volume 5, No. 4.
- [5] N.S. Apebo, M.B. Iorwua and J.C. Agunwamba "Comparative Analysis Of The Compressive Strength Of Concrete With Gravel And Crushed Over Burnt Bricks As Coarse Aggregates", Nigerian Journal of Technology, (2013), Vol. 32, No. 1, ISSN 1115-8443.
- [6] N. S. Apebo, J.C. Agunwamba, J.C. Ezeokonkwo. "The suitability of crushed over burnt bricks as coarse aggregates for concrete", International Journal of Engineering Science and Innovative Technology (IJESIT), (2014), Volume 3, Issue 1.
- [7] K Praveen, Dhanya Sathyan and K M Mini "Study on Performance of Concrete with Over - Burnt Bricks Aggregates and Micro - Silica Admixture", IOP Publishing, (2016), doi:10.1088/1757-899X/149/1/012061.
- [8] Rekha Kasi and Potharaju Malasani "Usage of Recycled Brick as Coarse Aggregate in Concrete", International Advanced Research Journal in Science, Engineering and Technology, (2016), Volume 3, Issue 9.
- [9] Ghanim Hussein Qoja and Youkhanna Zayia Dinkha "Performance of Concrete Made with Crushed Clay Bricks as Coarse Aggregate", Journal of University of Duhok, Vol. 20, No.1 (Pure and Eng. Sciences), Pp 561-569, 2017.
- [10] Nilesh Kumar, Anil Kumar Saxena and Gourav Soni "Analysis on Concrete Made from Over Burned Bricks", International Journal of Advance Research, Ideas and Innovations in Technology, (2017), Volume 3, Issue 6.
- [11] Bektas F., Wang K., Ceylan H., Effects of crushed clay brick aggregate on mortar durability. Construction and Building Materials, Vol. 23, 1909-1914, (2009).
- [12] Bhattacharjee, E., Nag, D., Sarkar, P. P. and Haldar, L. An Experimental Investigation of Properties of Crushed over Burnt Brick Aggregate Concrete. International Journal of Engineering Research and Technology, Volume 4, pp. 21-30, (2011).
- [13] Bingol A. F., Rustemgul, Effect of elevated temperatures and cooling regimes on normal strength concrete, Fire and Materials, Vol.33, Issue 2, pp. 79-88, (March 2009).
- [14] Cachim P.B., "Mechanical Properties of Brick Aggregate Concrete", Construction and Building Materials, Vol. 23, pp. 1292-1297, (2009).
- [15] Chandan Kumar, Krishna Murari, C.R.Sharma, Effect of Elevated Temperature and Aggressive Chemical Environment on Compressive Strength of M-30 Grade of Concrete Composite, Int. Journal of Engineering Research and Applications, Vol. 4, Issue 5( Version 2), pp. 151-157 (May 2014).
- [16] Chi Sun Poon, Dixon Chan, Feasible use of recycled concrete aggregates and crushed clay brick as unbound road sub-base. Construction and Building Materials, Vol. 20, pp. 578-585, (2006).
- [17] Chi Sun Poon, Dixon Chan, Paving blocks made with recycled concrete aggregate and crushed clay brick. Construction and Building Materials Vol. 20, pp. 569-577, (2006).
- [18] Chowdhury S.H., Effect of elevated temperature on mechanical properties of high strength concrete, 23rd Australasian Conference on the Mechanics of Structures and Materials, Vol. 9-12, pp. 1077 - 1082, (2014).
- [19] Cui H. Z., Xian Shi., Shazim Ali Memon., Feng Xing., Waiching Tang., Experimental study on the Influence of Water Absorption of Recycled Coars

### IS CODES:

- i. **IS 456 : 2000** -Plain and Reinforced Concrete Code of Practice. - BUREAU OF INDIAN STANDARDS, NEW DELHI.